



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
06.10.1999 Bulletin 1999/40

(51) Int Cl.⁶: **C08L 83/07, C08L 83/04,
C09J 183/04**

(21) Application number: **94305992.3**

(22) Date of filing: **12.08.1994**

(54) **Silicone rubber with self-adhesion to glass and metal**

An Glass oder Metall selbstklebender Siliconkautschuk

Caoutchouc de silicone auto-adhésif au verre et métal

(84) Designated Contracting States:
DE FR GB IT

(30) Priority: **17.08.1993 US 107494**

(43) Date of publication of application:
22.02.1995 Bulletin 1995/08

(73) Proprietor: **DOW CORNING CORPORATION**
Midland Michigan 48686-0994 (US)

(72) Inventors:
• **Gray, Thomas Edward**
Midland, Michigan (US)
• **Kunselman, Michael E.,**
Lucky-DC Silicone Co., Ltd.
Jinchon-Kun, Choongchungbuk-Do (KR)

• **Palmer, Richard Alan**
Midland, Michigan (US)

(74) Representative: **Hall, Marina**
Elkington and Fife
Prospect House,
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)

(56) References cited:
EP-A- 0 350 951 EP-A- 0 543 401
EP-A- 0 581 504 EP-A- 0 596 534
EP-A- 0 606 971
• **DATABASE WPI Derwent Publications Ltd.,**
London, GB; AN 89-140835 & JP-A-01 085 224
(TORAY SIKICONE KK) , 30 March 1989

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention relates to liquid silicone compositions curable to rubber. The cured rubber has a unique combination of properties including unprimed adhesion to a variety of substrates, such as glass and stainless steel.

[0002] Liquid silicone compositions curable to rubber based upon vinyl-containing polydiorganosiloxane polymer, organohydrogensiloxanes having silicon-bonded hydrogen atoms and platinum catalyst are well known in the art of silicone elastomer compositions. Such compositions are also well known for their reluctance to adhere to substrates on which the composition is cured. Many additives have been developed to improve adhesion of such compositions to a variety of substrates. However, the additives are, for the most part, selective to compositions and substrates in which they are effective. Many approaches are found in the prior art to solve the problem of adhering such addition-curable silicone compositions to substrates. Some solutions use the primer approach and others use the adhesion promoter approach. While each of these approaches have merit, their solutions do not provide the rapid cure needed at low temperatures, good adhesion to both glass and stainless steel substrates and bond durability under adverse conditions.

[0003] The prior art for various combinations of catalysts and adhesion promoters, primer compositions or other self-bonding additives is represented by US-A 4,332,844; 4,659,851; 4,719,262; 4,737,562; 4,754,013; 4,906,686; 5,006,580 and 5,023,288.

[0004] This invention provides a silicone composition curable to a rubber comprising


(A) 100 parts by weight of an alkenyl-containing polydiorganosiloxane having an average of at least two silicon-bonded alkenyl radicals per molecule where the alkenyl radical has from 2 to 10 inclusive carbon atoms per radical, each organo radical of the polydiorganosiloxane being a monovalent radical selected from the group consisting of hydrocarbon radicals and fluorinated alkyl radicals both having less than 7 carbon atoms per radical, the polydiorganosiloxane having triorganosiloxy endgroups,

(B) an organohydrogensiloxane having an average of at least 3 silicon-bonded hydrogen atoms per molecule and valences of any silicon atom in the organohydrogensiloxane not satisfied by a hydrogen atom is satisfied by a divalent oxygen atom or an organo radical wherein each organo radical is a monovalent radical selected from the group consisting of hydrocarbon radicals and fluorinated alkyl radicals both having less than 7 carbon atoms per radical, the organohydrogensiloxane having no more than one silicon-bonded hydrogen atom on any one silicon atom, the amount of organohydrogensiloxane providing a ratio of silicon-bonded hydrogen atoms to alkenyl groups from the polydiorganosiloxane of 1.2 to 2,

(C) a hydrosilation catalyst containing platinum,

(D) 0.1 to 1 part by weight of an (epoxy-functional organo)trialkoxysilane where the alkoxy radicals of the (epoxy-functional organo)trialkoxysilane have 1 to 4 inclusive carbon atoms,

(E) 0.25 to 5 parts by weight of an alkoxyisilicon compound selected from tetraalkyl orthosilicates, alkylpolysilicates and alkoxyisilicon compounds of the general formula



wherein n is 0 or 1, R is an alkyl radical of 1 to 4 inclusive carbon atoms and R' is a monovalent hydrocarbon radical, where the alkyl groups of the tetraalkyl orthosilicates and the alkylpolysilicates are methyl, ethyl, propyl or butyl, and

(F) 0.01 to 0.5 part by weight of a titanium compound having Ti-O-CH bonds,

where the total amount of ingredient (D) and ingredient (E) is from 0.5 to 6 parts by weight and the molar amount of (E) exceeds the molar amount of (D).

[0005] Another embodiment of this invention is a method of adhering a glass substrate to a stainless steel substrate comprising

(1) mixing


(A) 100 parts by weight of an alkenyl-containing polydiorganosiloxane having an average of at least two silicon-bonded alkenyl radicals per molecule where the alkenyl radical has from 2 to 10 inclusive carbon atoms per radical, each organo radical of the polydiorganosiloxane being a monovalent radical selected from the group consisting of hydrocarbon radicals and fluorinated alkyl radicals both having less than 7 carbon atoms per radical, the polydiorganosiloxane having triorganosiloxy endgroups,

(B) an organohydrogensiloxane having an average of at least 3 silicon-bonded hydrogen atoms per molecule and valences of any silicon atom in the organohydrogensiloxane not satisfied by a hydrogen atom is satisfied by a divalent oxygen atom or an organo radical wherein each organo radical is a monovalent radical selected from the group consisting of hydrocarbon radicals and fluorinated alkyl radicals both having less than 7 carbon atoms per radical, the organohydrogensiloxane having no more than one silicon-bonded hydrogen atom on any one silicon atom, the amount of organohydrogensiloxane providing a ratio of silicon-bonded hydrogen atoms to alkenyl groups from the polydiorganosiloxane of 1.2 to 2,

(C) a hydrosilation catalyst containing platinum,

(D) 0.1 to 1 part by weight of an (epoxy-functional organo)trialkoxysilane where the alkoxy radicals of the (epoxy-functional organo)trialkoxysilane have 1 to 4 inclusive carbon atoms,

(E) 0.25 to 5 parts by weight of an alkoxy silicon compound selected from tetraalkyl orthosilicates, alkylpoly-silicates and alkoxy silicon compounds of the general formula



wherein n is 0 or 1, R is an alkyl radical of 1 to 4 inclusive carbon atoms and R' is a monovalent hydrocarbon radical, where the alkyl groups of the tetraalkyl ortho silicates and the alkylpolysilicates are methyl, ethyl, propyl or butyl, and

(F) 0.01 to 0.5 part by weight of a titanium compound having Ti-O-CH bonds,

where the total amount of ingredient (D) and ingredient (E) is from 0.5 to 6 parts by weight and the molar amount of (E) exceeds the molar amount of (D), to make a curable silicone rubber composition,

(2) applying the curable silicone rubber composition to a glass substrate and a stainless steel substrate such that the glass and stainless steel substrates are connected by curable silicone rubber composition making an assembly, and thereafter

(3) maintaining the assembly in position until the silicone rubber composition has cured thereby bonding the glass substrate to the stainless steel substrate through cured silicone rubber.

[0006] Our invention broadly relates to a silicone composition curable to rubber comprising an alkenyl-containing polydiorganosiloxane having an average of at least two silicon-bonded alkenyl groups per molecule, an organohydrogensiloxane having an average of at least 3 silicon-bonded hydrogen atoms per molecule, a hydrosilation catalyst containing platinum and additives which promote the adhesion to substrates against which it is cured, especially glass and stainless steel. It is our selection of additives which provide the adhesion characteristics and the bond durability over extended periods of time. Moreover, our additives do not deteriorate other cure properties, nor mechanical and chemical properties, such as fast curing at low temperatures and heat accelerated curing. Thus, our claimed compositions are curable in less than 5 minutes at 80°C. or in one to two hours at room temperature.

[0007] Our silicone compositions are dispensed onto substrates while uncured and are then cured in place. They are required to adhere to substrates which may be metal or glass. By extensive investigation, we have found that certain combinations of additives in specific amounts can be added to silicone compositions to produce adhesion to substrates upon which they are cured. In silicone compositions curable by hydrosilation reactions, the ratio of hydrogen on silicon to alkenyl on silicon is controlled within certain limits to accommodate the adhesion additives and to produce a unique combination of adhesion and cure properties.

[0008] To enhance the adhesion of our cured rubbers to substrates, the silicone composition of this invention comprises a titanium compound, an alkoxy silicon compound, an (epoxy-functional organo)trialkoxysilane and, optionally, unsaturated silanes such as gamma-methacryloxypropyltrialkoxysilane and/or unsaturated non-silicon containing ethers such as diallyl ether of trimethylolpropane. The combination of these components in controlled amounts is found


important in providing sufficient initial adhesion to substrates such as glass and stainless steel and in providing rapid cure between ambient temperatures and 100°C. This combination also provides wet adhesion that is significantly improved over various prior art adhesion additives. Compositions containing these components is found particularly useful for use with glass and metal substrates, such as stainless steel.

[0009] Ingredient (A) of the silicone composition of our invention is primarily a linear polymer of one or more alkenyl-containing polydiorganosiloxanes containing at least two alkenyl groups having from 2 to 10 carbon atoms such as vinyl, allyl, 3-butenyl, 4-pentenyl, 5-hexenyl, 7-octenyl and/or 9-decenyl groups. For the polymer to properly crosslink, at least 2 alkenyl groups per molecule are needed. Generally the polydiorganosiloxane is diorganoalkenylsiloxy terminated with an alkenyl group such as a vinyl group. The alkenyl radical contains at least two carbon atoms and can be represented by the formula $-R_sCH=CH_2$, where R represents an alkylene radical containing from 1 to 8 carbon atoms and s is 0 or 1. The alkylene radical can be linear or branched. The preferred alkenyl groups are vinyl and hexenyl. Polydiorganosiloxanes which have a combination of vinyl and hexenyl are preferred because the ratio of the hexenyl to vinyl can be used to regulate the rate of cure. For example, an increase in the amount of hexenyl containing polydiorganosiloxane in ingredient (A) will accelerate the rate of cure.

[0010] The organo groups of the polydiorganosiloxane are individually monovalent hydrocarbon radicals or fluorinated monovalent hydrocarbon radicals containing from 1 to 6 carbon atoms. The organo radicals can be identical or different, such as methyl or ethyl, fluorinated alkyl such as 3,3,3-trifluoropropyl, cycloalkyl such as cyclohexyl or aryl such as phenyl. A preferred radical is the methyl radical.

[0011] Generally the siloxane is polymerized to achieve a viscosity of from 2 to 100 Pa·s at 25°C., preferably from 2 to 50 Pa·s. It is also possible to use either higher or lower viscosity polymers.

[0012] A single polydiorganosiloxane, or a mixture of different polymers, can be used. Ingredient (A) can be a mixture of polydiorganosiloxanes which includes as a second polymer a liquid diorganoalkenylsiloxy-terminated polydiorganosiloxane that is represented by the average general formula



wherein R^3 represents a terminally unsaturated alkenyl radical containing at least four, preferably at least six, carbon atoms and R^4 is selected from the same group of monovalent hydrocarbon radicals and fluorinated monovalent hydrocarbon radicals as the polydiorganosiloxane above. The preference for six carbon atoms for R^3 is based on the availability of the starting material, typically the corresponding chlorosilane, for preparing polydiorganosiloxanes containing this radical bonded to a portion of the silicon atoms. R^3 can be represented by the general formula $-R''CH=CH_2$, where R'' represents an alkylene radical containing at least 2, and preferably at least 4, carbon atoms. The radical represented by R'' can be linear or branched. Examples of R^3 include 3-butenyl, 4-pentenyl, 5-hexenyl, 7-octenyl, 9-decenyl and 9-decenyl. Methods for preparing the polydiorganosiloxanes are sufficiently disclosed in patents and other literature such that a detailed description is unnecessary.

[0013] The physical properties of the cured rubber are affected by the polymer size, viscosity and the amount of crosslinking. For example, use of polymer mixtures having one polymer with only terminal vinyl groups and another polymer with both terminal and pendant vinyl groups is taught in US-A 4,753,978. The use of an alkenyl radical having at least 4 carbon atoms is taught in US-A(s) 4,946,878 and 5,110,845. These patents show polydiorganosiloxanes and their mixtures which can be used in this invention.

[0014] In addition to ingredient (A), an alkenyl-containing siloxane resin can be present in the composition. Such siloxane resins can be used to increase the tensile strength and the tear strength of our silicone compositions. Examples of these siloxane resins are made up of the following siloxane units, $ViMe_2SiO_{0.5}$, $Me_3SiO_{0.5}$ and $SiO_{4/2}$ where the ratio of $ViMe_2SiO_{0.5}$ and $Me_3SiO_{0.5}$ units to $SiO_{4/2}$ units is from 0.4:1 to 1.2:1 and the amount of vinyl group is from 1.5 to 3.5 weight percent, based on the weight of siloxane resin. Amounts can be widely varied, but are usually less than 50 weight percent of the weight of the curable silicone composition.

[0015] The crosslinking agent, (B), is an organohydrogensiloxane containing an average of at least three silicon-bonded hydrogen atoms per molecule. The organohydrogensiloxane contains from as few as four silicon atoms per molecule up to an average of 100 or more and can have a viscosity of 10 Pa·s or higher at 25°C. The repeating units of this ingredient include $HSiO_{1.5}$, R^1HSiO and/or $R^1_2HSiO_{0.5}$ in addition to one or more of $R^1SiO_{1.5}$, R^1_2SiO , $R^1_3SiO_{0.5}$ and $SiO_{4/2}$ units. In these formulae, R^1 represents a monovalent hydrocarbon or fluorinated radical as defined above for R^4 of the polydiorganosiloxane.

[0016] The organohydrogensiloxane can be linear copolymer of diorganosiloxane units and organohydrogensiloxane units end-blocked with triorganosiloxy units or monohydrogendiolorganosiloxy units, a cyclic compound containing both diorganosiloxane and organohydrogensiloxane units or a compound of the formula $Si(OSiR^4_2H)_4$.

[0017] Proper curing of the present composition requires that the polydiorganosiloxane (A), organohydrogensiloxane (B) and hydrosilation catalyst (C) be miscible with one another. To ensure sufficient miscibility, it is preferred that a

majority of the silicon-bonded hydrocarbon radicals present in the polydiorganosiloxane and the organohydrogensiloxane be selected from the same class, e.g. alkyl radical. In particularly preferred compositions, these hydrocarbon radicals are methyl or combinations of methyl with either 3,3,3-trifluoropropyl or phenyl.

[0018] The molar ratio of silicon-bonded hydrogen atoms to alkenyl radical (vinyl or other ethylenically unsaturated hydrocarbon radicals) in compositions curable by hydrosilation reaction is important to the properties of the cured elastomer. The optimum ratio for our compositions is determined at least in part by the molecular weight of the polydiorganosiloxane and the type of curing agent. An effective molar ratio of silicon-bonded hydrogen atoms to silicon-bonded alkenyl radicals is in the range of 1.2 to 2 with a preferred range of 1.6 to 2.

[0019] Hydrosilation reactions are typically conducted in the presence of a catalyst containing platinum. Platinum compounds such as hexachloroplatinic acid, and particularly complexes of these compounds with relatively low molecular weight vinyl-containing organosiloxane compounds, are preferred catalysts because of their high activity and compatibility with the organosiloxane reactants. These complexes are more fully described in US-A 3,419,593.

[0020] The platinum-containing catalyst can be present in an amount equivalent to as little as one part by weight of platinum per one million parts by weight of curable composition. Catalyst concentrations equivalent to from 5 to 100 parts of platinum per million of curable composition are preferred to achieve a practical curing rate. Higher concentrations of platinum provide only marginal improvement in curing rate and are therefore economically unattractive.

[0021] Mixtures of the aforementioned polydiorganosiloxane, organohydrogensiloxane (crosslinking agent) and platinum catalyst may begin to cure at ambient temperatures. It is therefore desirable to package the ingredients in at least two separate containers. Usually a first container comprises the alkenyl-containing polydiorganosiloxane and platinum catalyst and a second container comprises the polyorganohydrogensiloxane. Although a rapid cure rate is desired for the present invention, in certain situations one may wish to slow the curing reaction down to room temperature. If this is desired, the addition reaction catalyzed by the platinum catalyst can be slowed by adding an inhibitor such as those which are known to inhibit the hydrosilation reaction at room temperatures. Longer working time or "pot life", can be obtained by the addition of a suitable inhibitor. Known inhibitors include the acetylenic compounds disclosed in US-A 3,445,420. Acetylenic alcohols such as 2-methyl-3-buten-2-ol and ethynyl cyclohexanol constitute a preferred class of inhibitors that will suppress the activity of a platinum-containing catalyst at 25°C., but will also cure rapidly at temperatures of 70°C. or higher.

[0022] To obtain satisfactory levels of physical strength, our silicone compositions comprising polydiorganosiloxane can also contain a particulate filler. Silicone compositions are commonly reinforced with one or more fillers such as fumed silica. Any finely divided form of silica can be used herein as a reinforcing filler. Colloidal silicas are preferred because of their relatively high surface area, which is typically at least 50 square meters per gram. Fillers having surface areas of at least 250 square meters per gram are preferred for use in the present method. Colloidal silicas can be prepared by precipitation or a fume process. Both of these types of silica are commercially available.

[0023] The amount of finely divided silica used in our compositions is at least in part determined by the physical properties desired in the cured rubber. Liquid or pumpable silicone compositions typically contain from 10 to 60 percent by weight of silica, based on the weight of polydiorganosiloxane.

[0024] Preferably, if reinforcing filler is used, it is modified with silica treating agents to prevent a phenomenon referred to as "creeping" or "crepe hardening" during processing of the curable composition and to provide a product which has greater stability during storage. These silica treating agents can be liquid hydroxyl terminated polydiorganosiloxanes containing an average of from 2 to 20 repeating units and can contain an alkenyl radical. Treating agents can also be organosilicon compounds such as hexaorganodisiloxanes and hexaorganodisilazanes such as hexamethyldisilazane. They can also hydrolyze under the conditions used to treat the silica to form compounds with silicon-bonded hydroxyl groups. Small amounts of water are often added to the composition during the filler treatment step to facilitate the process.


[0025] The filler can also be a non-reinforcing or extending filler of finely ground particles of oxides or hydroxides or carbonates of such as silicon, calcium, magnesium, barium or zinc, with silicon oxide (quartz) and calcium carbonate as preferred non-reinforcing fillers. Suitable fillers for silicone elastomeric compositions are well known in the art.

[0026] The (epoxy-functional organo)trialkoxysilane ingredient (D) is a trialkoxysilane functionalized with an organic substituent containing an epoxy group. Typically the alkoxy radicals of the (epoxy-functional organo) trialkoxysilane may be the same or different and are usually selected from alkoxy radicals having 1 to 4 carbon atoms such that the alkoxy radicals are readily hydrolyzable upon contact with water. For example, the alkoxy radicals may include methoxy, ethoxy, propoxy and butoxy. The structure of the organic substituent bearing the epoxy group may vary. Commercially available (epoxy-functional organo) trialkoxysilanes useful herein include 3-glycidoxypropyltrimethoxysilane and beta-(3,4-epoxycyclohexyl) ethyltrimethoxysilane. 3-glycidoxypropyltrimethoxysilane is preferred because of its effectiveness.

[0027] The amount of ingredient (D) used is typically 0.1 to 1 part by weight per 100 parts by weight of polydiorganosiloxane in the composition. Both dry and wet adhesion of the cured silicone rubber to substrates increases with increased amounts of ingredient (D). Amounts of ingredient (D) exceeding one part by weight per 100 parts by weight

of ingredient (A) may be detrimental to the adhesion properties of the cured silicone rubber to glass and metal substrates. Preferred silicone compositions of this invention contain 0.2 to 0.5 part by weight of ingredient (D) per 100 parts by weight of ingredient (A).


[0028] The alkoxysilicon compound, ingredient (E), can be an alkyl orthosilicate or a partially hydrolyzed alkyl orthosilicate where the alkyl groups have up to 4 carbon atoms. The alkyl groups may be the same or different. Alkyl orthosilicates include ethyl orthosilicate, methyl orthosilicate, n-propyl orthosilicate and butyl orthosilicate. The partial hydrolyzed alkyl orthosilicates are also known as alkylpolysilicates which include ethylpolysilicate, n-propylpolysilicate and butylpolysilicate. Alkoxysilicon compound (E) can also be a compound of the general formula



wherein n is 0 or 1, R is an alkyl radical of 1 to 4 inclusive carbon atoms, such as methyl, ethyl, propyl and butyl and R' is a monovalent hydrocarbon radical selected from alkyl, such as methyl, ethyl and hexyl and aryl such as phenyl.

[0029] Preferably, both R and R' are methyl. The alkoxysilicon compound is present in an amount of 0.25 to 5 parts by weight per 100 parts by weight of ingredient (A). It is preferred for improved adhesion to use from 0.4 to 3 parts of ethylpolysilicate or n-propyl orthosilicate. The combined amount of (epoxy-functional organo)trialkoxysilane and alkoxysilicon compound should be at least 0.5 part by weight per 100 parts by weight of ingredient (A), preferably from 0.5 to 6 parts by weight. It is also necessary to have the molar amount of alkoxysilicon compound (E) exceed the molar amount of (epoxy-functional organo)trialkoxysilane to provide satisfactory adhesion. If both the (epoxy functional organo)trialkoxysilane and the alkoxysilicon compound are at their lower limits, poor adhesion is obtained.

[0030] The silicone compositions of this invention further include a titanium compound having Ti-O-CH bonds, (F). These titanium compounds aid in the shortening of time for development of adhesion between the cured silicone rubber and the substrates. Examples of titanium compounds include tetra-alkyl titanates such as tetraisopropyl titanate, tetrabutyl titanate and tetraoctyl titanate, tetraisopropyl titanate and tetra-2-ethylhexyl titanate; chelated titanates such as



and other titanium compounds such as $(CH_2CH_2CH_2O)_3TiTi(OCH_2CH_2CH_3)_3$. The amounts of titanium compound (F) can be from 0.01 to 0.5 part by weight per 100 parts by weight of ingredient (A), preferably from 0.05 to 0.3 part by weight.

[0031] The silicone compositions of this invention can optionally contain an olefinically unsaturated alkoxy silane, (G). These alkoxy silanes are illustrated by gamma-methacryloxypropyltrialkoxysilane, vinyltrialkoxysilane and hexenyltrialkoxysilane, in which the alkoxy groups preferably contain from 1 to 4 carbon atoms per alkoxy group, such as methoxy, ethoxy, propoxy and butoxy. These olefinically unsaturated alkoxy silanes are present in amounts up to 1 weight percent based on the weight of the silicone composition, preferably from 0.1 to 1 weight percent.

[0032] The silicone compositions of this invention can also optionally contain an unsaturated non-silicon-containing ether, (H). Examples are diallyl ether of trimethylolpropane, monoallyl ether of trimethylolpropane, monoallyl ether of glycerol, diallyl ether of glycerol, monoallyl ether of ethylene glycol, monoallyl ether of diglycerol, diallyl ether of diglycerol, monoallyl ether of pentaerythritol, diallyl ether of pentaerythritol and triallyl ether of pentaerythritol. If an unsaturated non-silicon-containing ether is used, it is preferably diallyl ether of trimethylolpropane. The amount of unsaturated non-silicon-containing ether used can effect the length of cure at lower temperatures. For this reason, small amounts of this ether is preferably used when it is desired to have it present. Such amounts are up to 1.5 weight percent based on the weight of the silicone composition and preferred amounts are from 0.1 to 1.2 weight percent. These unsaturated non-silicon-containing ethers also provide silicone compositions with increased adhesive tensile strengths

for the cured product. Therefore, one balances the value of curing time of the silicone composition versus the enhanced adhesive tensile strength for the cured product for their particular application. For example, if fast cure is desired or required, the unsaturated non-silicon-containing ether may be left out of the silicone composition. If the adhesive tensile strength of the cured product is more important to the particular application, then the unsaturated non-silicon-containing ether may be used despite the slow cure rate. Of course, if smaller amounts of the unsaturated non-silicon-containing ether are used, one may improve the adhesive tensile strength of the cured product and also maintain a reasonable curing time for the silicone composition at lower temperatures.

[0033] It is preferred to keep the titanium compound (F) separated from ingredient (B) during storage. Therefore, the most preferred silicone compositions are those which are packaged in at least two containers. These preferred silicone compositions are stored by packaging in a first container which comprises ingredients (F) and (C) and in a second container which comprises ingredient (B). Convenient packaging for the silicone compositions of this invention are a first container in which ingredients (A), (C), (F) and a particulate filler, if used, are present; and a second container in which ingredients (B), (D) and (E) are present. It is also possible to divide ingredient (A) and particulate filler and to place portions of both in the first and second containers. When unsaturated non-silicon-containing ethers are used, it is preferred to include such ethers in a first container with ingredients (F) and (C) for maximum storage stability. This will achieve the best results during curing and the best results for the properties of the cured products.

[0034] In addition to the above ingredients, our silicone composition may include conventional additives which impart or enhance certain properties of the cured elastomer or facilitate processing of the curable composition. Typical additives include pigments, dyes and heat and/or ultraviolet light stabilizers. The effect of any such additives should be evaluated as to their result and impact on other desirable properties of the composition.

[0035] The compositions of this invention can be prepared by a simple mixing of the ingredients. However, when reinforcing fillers are included, the fillers are often treated in situ by first combining the polydiorganosiloxane, filler, filler treating agent and enough water to facilitate the filler treating process and then heating the mixture. Heating for 1 to 4 hours at 170°C. has been found to provide good filler treatment. The heating may also be conducted at reduced pressure to assist in removing any excess water and the ammonia formed in the process. After filler treatment is completed the remaining components are simply mixed into the composition. The equipment needed for the mixing depends upon the viscosity of the polydiorganosiloxane used and the amount of filler.

[0036] When all of the ingredients are mixed together, the composition will begin to cure unless a cure inhibitor is present. If the composition is not to be used immediately after mixing, it should be prepared in at least two parts. If the organohydrogensiloxane, (B), is placed in one part and the platinum catalyst, (C), and the titanium compound, (F), is placed in another part, the individual parts will be shelf stable. The amounts of polydiorganosiloxane and filler that are placed in each part can be varied to obtain the desired result. A convenient system distributes the ingredients into two parts so that the polydiorganosiloxane and filler are divided equally between the two parts. The organohydrogensiloxane is added to one part and the platinum catalyst plus the titanium compound are added to the other part. This results in a two-package composition where the contents of the two packages are mixed together in equal amounts at the time of ultimate use. If the consistency of the two parts is about the same, they can be easily mixed at the time of use. Other proportions of the ingredients can of course be used, as well as more than two parts, if desired.

[0037] For application, the contents of the two packages of the silicone composition are mixed together and are extruded into place on at least one substrate to be adhered as a bead. After the bead is formed on the substrate or substrates to be adhered, it is allowed to cure at ambient temperatures or it can be heated to accelerate the cure. The bead adheres to the substrate upon curing. The silicone compositions of this invention adhere very well to stainless steel and glass substrates when the silicone composition is cured in contact with such substrates. Adhesion of the silicone composition to other substrates against which it is cured are also acceptable.

[0038] The silicone compositions of this invention develop adhesion without the use of primers when the composition is cured against a substrate. These silicone compositions can be cured rapidly at low temperatures, such as from room temperature to 80°C. At room temperature, the silicone compositions can be cured in one or two hours, but at 80°C., it can be cured in less than five minutes. The rubber obtained by curing the composition exhibits both dry and wet adhesion to the substrates. Dry adhesion is determined by measuring the adhesion of a substrate-rubber test piece over a defined period of time at a defined temperature. Wet adhesion is determined by measuring the adhesion of a substrate-rubber test piece which has been immersed in water for a defined period of time at a defined temperature.

[0039] The silicone compositions can cure against substrates and develop sufficient initial adhesion to allow handling of articles which are bonded together using the silicone composition to bond substrates, such as glass and stainless steel. The cured silicone rubber also has sufficient tensile strength so that together with the initial adhesion between the silicone rubber and the substrates, an article can be handled without concern of deforming the article. This tensile strength-initial adhesion characteristic is termed "green strength" or initial tensile-adhesion. The cured silicone rubber should also maintain the tensile strengths throughout the useful lifetime of the adhesive-substrate bond. The silicone rubber obtained by curing the composition of this invention also exhibits low thermal conductivity.

[0040] A bubbling phenomenon at some substrate-rubber interfaces was observed with certain types of adhesion

additives and when the titanium compound (F) and unsaturated non-silicon-containing ether (H) were stored in a package with the organohydrogensiloxane (B). One substrate against which the silicone composition was cured which was susceptible to such a bubbling phenomenon was polyisobutylene. Bubbling at a rubber-substrate interface means weak spots and reduced effectiveness of the seals which are intended by the use of the silicone composition with unprimed adhesion to substrates. During the development of this invention, bubbling was observed when an attempt was made to pre-react the titanium compound (F), the alkoxysilicon compound (E) and the (epoxy-functional organo)-trialkoxysilane (D). Also when the unsaturated non-silicon-containing ether was used with (F), (E) and (D) and the mixture was pre-reacted, bubbling was still observed at rubber-substrate interfaces. The presence of amino compounds in the silicone composition results in gassing and the wet adhesion is very poor. Therefore, although aminosilicon compounds have been reported as adhesion promoters, they do not function acceptably in our compositions.

[0041] The following examples are included for illustrative purposes only and should not be construed as limiting the invention which is properly set forth in the appended claims. Parts are parts by weight.

Example 1

[0042] Two-package compositions were prepared for use in evaluating various adhesion additives. The contents of each package was prepared as defined below.

Adhesion Additive Composition No. 1 (AAC No. 1)


[0043] Package A was prepared by mixing 92.8 parts of dimethylvinylsiloxy endblocked polydimethylsiloxane having a viscosity of 55 Pa-s at 25°C. as measured by a rotational viscometer with a spindle number 5 at 4 rpm (Polymer A), 7.2 parts of a dimethylhexenylsiloxy endblocked poly(dimethylsiloxanehexenylmethylsiloxane) having 2 mole percent hexenylmethylsiloxane units and a viscosity at 25°C. of 0.45 Pa-s (Polymer B), 20.5 parts of a hexamethyldisilazane treated fumed silica filler having a surface area of 400 m²/g (Silica), 0.5 part of a platinum catalyst which was a reaction product of hexachloroplatinic acid and sym-tetramethyldisiloxane diluted with a liquid dimethylvinylsiloxy terminated polydimethylsiloxane in an amount to achieve a platinum content of 0.7 weight percent (Platinum Catalyst) and 0.3 part of tetrabutyltitanate (TBT).

[0044] Package B was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 9.5 parts of trimethylsiloxy endblocked poly(dimethylsiloxanemethylhydrogensiloxane) having an average of 3 dimethylsiloxane units and 5 methylhydrogensiloxane units per molecule (SiH Polymer), 4.2 parts of ethylpolysilicate, 0.7 part of gamma-glycidoxypolytrimethoxysilane and 2.4 parts of diallyl ether of trimethylolpropane.

Comparative Adhesion Addition Composition No. 1 (CAAC No.1)

[0045] Package A was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 0.5 part of Platinum Catalyst, 0.3 part of TBT.

[0046] Package B was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 9.4 parts of SiH Polymer, 4.8 parts of an alkoxysilicon compound of the formula



and 2.4 parts of diallyl ether of trimethylolpropane.

Comparative Adhesion Additive Composition No. 2 (CAAC No.2)

[0047] Package A was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 0.5 part of Platinum Catalyst, 2.4 parts of gamma-glycidoxypolytrimethoxysilane and 1.2 parts of gamma-methacryloxypropyltrimethoxysilane.

[0048] Package B was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 4.6 parts of SiH Polymer and 0.4 part of aluminum acetylacetonate added as a 5 percent by weight solution of aluminum acetylacetonate in toluene.

Comparative Adhesion Additive Composition No. 3 (CAAC No.3)

[0049] Package A was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 0.5 part of Platinum Catalyst, 0.7 part of allyltrimethoxysilane and 0.3 part of TBT.

[0050] Package B was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of silica and 4.5 parts of SiH polymer.

Comparative Adhesion Additive Composition No. 4 (CAAC No.4)

[0051] Package A was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 0.5 part of Platinum Catalyst and 0.3 part of TBT.

[0052] Package B was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of Silica, 5.1 parts of SiH Polymer, 2.4 parts of gamma-methacryloxypropyltrimethoxysilane and 0.7 part of diallyl ether of trimethylolpropane.

Comparative Adhesion Additive Composition No. 5 (CAAC No.5)

[0053] Package A was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of silica and 0.5 part of Platinum Catalyst.

[0054] Package B was prepared by mixing 92.8 parts of Polymer A, 7.2 parts of Polymer B, 20.5 parts of silica and 3.3 parts of SiH Polymer.

[0055] Each of the above compositions were evaluated by mixing 50 weight parts of the contents of Package A with 50 weight parts of the contents of Package B and then curing on stainless steel and glass substrates for one hour at 80°C. The adhesion for the stainless steel substrates was determined by using a lap shear test with the results being reported in kilopascals (kPa). The lap shear test evaluated the adhesion of the silicone rubber to the stainless steel substrates by making test laminates by placing a bead of silicone composition between two panels of stainless steel, such that the panels with silicone composition laminated between them overlapped by 6.4 square centimeters. The silicone composition was cured for one hour at 80°C. and then after a defined period of time as shown in Table 1, the panels were pulled in opposite directions. The force at which the silicone rubber-stainless steel laminate broke was recorded in kPa and reported in Table 1. The adhesion for the glass substrate was determined by Tensile-Adhesion joint construction as specified in ASTM Test Method C 1135-90, "Standard Test Method for Tensile Adhesion Properties of Structural Sealants." The Tensile-Adhesion results were obtained on laminates in which the silicone rubber composition was 1.27 cm by 1.27 cm by 5.08 cm. The pull rate was 1.27 cm per minute and the results are reported in Table 1 in kPa. Each silicone rubber composition was tested three times and the average of these tests was used for each value reported. The adhesion for each kind of laminate was evaluated 24 hours after the silicone composition was cured, 2 weeks after being immersed in water at 80°C. and 4 weeks after being immersed in water at 80°C. The results are shown in Table 1.

TABLE 1

COMPOSITION	SUBSTRATE	ADHESIVE STRENGTHS in kilopascals		
		AFTER 24 HRS	AFTER 2 WKS WATER IMMERSION	AFTER 4 WKS WATER IMMERSION
AAC No.1	GLASS*	1103	1103	931
	STAINLESS STEEL**	1379	1482	1641
CAAC No.1	GLASS*	419	1379	1379
	STAINLESS STEEL**	803	1379	1379
	GLASS*	517	793	276

* Adhesive strengths determined by Tensile-Adhesion Test.

** Adhesive strengths determined by Lap Shear Test.

EP 0 639 622 B1

TABLE 1 (continued)

COMPOSITION	SUBSTRATE	AFTER 24 HRS	ADHESIVE STRENGTHS in kilopascals	
			AFTER 2 WKS WATER IMMERSION	AFTER 4 WKS WATER IMMERSION
CAAC No.2	STAINLESS			
	STEEL**	2413	793	1276
CAAC No.3	GLASS*	552	517	310
	STAINLESS			
CAAC No.4	STEEL**	419	434	386
	GLASS*	241	310	276
CAAC No.5	STAINLESS			
	STEEL**	1172	965	965
	GLASS*	193	214	138
	STEEL**	103	228	103

* Adhesive strengths determined by Tensile-Adhesion Test.

** Adhesive strengths determined by Lap Shear Test.

[0056] CAAC No. 1 exhibited very good adhesion to both glass and stainless steel but was slow to develop adhesive strength.

[0057] CAAC No. 2 showed very good 24 hour adhesion to stainless steel and only fair adhesion to glass. The adhesion to both the stainless steel and the glass showed deterioration after hot water immersion.

[0058] CAAC No. 3 showed only minimal improvement in adhesion to both glass and stainless steel compared to CAAC No. 5 which contained no adhesion additive.

[0059] CAAC No. 4 exhibited very poor adhesion to glass and good adhesion to stainless steel.

[0060] CAAC No. 5 was a control which contained no adhesion additives.

Example 2

[0061] Two-package compositions were prepared for use in evaluating various adhesion additives in an assembly having glass and stainless steel substrates. The contents of each package was prepared with the ingredients as defined below.

Adhesion Additive Composition No. 2 (AAC No. 2)

[0062] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 0.36 part of platinum catalyst, 0.24 part of TBT and 1.2 part of diallyl ether of trimethylolpropane.

[0063] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 5.2 parts of SiH Polymer, 2.4 parts of ethylpolysilicate and 0.6 part of gamma-glycidoxypolytrimethoxysilane.

Adhesion Additive Composition No. 3 (AAC No. 3)

[0064] Package A was prepared as described for Package A of AAC No. 2.

[0065] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 5.2 parts of SiH Polymer, 2.1 parts of ethyl orthosilicate and 0.6 part of gamma-glycidoxypolytrimethoxysilane.

Adhesion Additive Composition No. 4 (AAC No. 4)

[0066] Package A was prepared as described for Package A of AAC No. 2.

[0067] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 5.2 parts of SiH polymer, 2.7 parts of n-propyl orthosilicate and 0.6 part of gamma-glycidoxypolytrimethoxysilane.


Adhesion Additive Composition No. 5 (AAC No. 5)

[0068] Package A was prepared as described for Package A of AAC No. 2.

[0069] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 5.2 parts of SiH polymer, 2.4 parts of ethylpolysilicate and 0.6 part of beta(3,4-epoxy-cyclohexyl)ethyltrimethoxysilane.

Adhesion Additive Composition No. 6 (AAC No. 6)

[0070] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 0.36 part of platinum catalyst, 1.2 part of diallyl ether of trimethylolpropane and 0.3 part of a Ti-O-CH compound of the formula



[0071] Package B was prepared as described for Package B of AAC No. 2.

Adhesion Additive Composition No. 7 (AAC No. 7)

[0072] Package A was prepared as described for Package A of AAC No. 2.

[0073] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 5.2 parts of a trimethylsiloxy endblocked polymethylhydrogensiloxane having an average of about 35 siloxane units per molecule, 2.4 parts of n-propyl orthosilicate and 0.6 part of gamma-glycidoxypropyltrimethoxysilane.

Adhesion Additive Composition No. 8 (AAC No. 8)

[0074] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of a dimethylvinylsiloxy endblocked poly(dimethylsiloxanemethylvinylsiloxane) having a viscosity of 0.3 Pa-s and a vinyl content of 1.15 weight percent (Polymer C), 17.9 parts of silica, 0.36 part of platinum catalyst, 0.24 part of TBT and 1.2 part of diallyl ether of trimethylolpropane.

[0075] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer C, 17.9 parts of silica, 5.2 parts of SiH polymer, 2.4 parts of ethylpolysilicate and 0.6 part of gamma-glycidoxypropyltrimethoxysilane.

Adhesion Additive Composition No. 9 (AAC No. 9)

[0076] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 0.36 part of platinum catalyst and 0.24 part of TBT. Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 2.8 parts of SiH Polymer, 2.6 parts of n-propyl orthosilicate, 0.6 part of gamma-glycidoxypropyltrimethoxysilane and 0.35 part of gamma-methacryloxypropyltrimethoxysilane.

Comparative Adhesion Additive Composition No. 6 (CAAC No. 6)

[0077] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 0.36 part of platinum catalyst and 1.2 part of diallyl ether of trimethylolpropane.

[0078] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 5.2 parts of SiH polymer, 2.4 parts of ethylpolysilicate and 0.6 part of gamma-glycidoxypropyltrimethoxysilane.

Comparative Adhesion Additive Composition No. 7 (CAAC No. 7)

[0079] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica and 0.36 part of platinum catalyst.

[0080] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 2.5

parts of SiH polymer and 0.6 part of gamma-glycidoxypolytrimethoxysilane.

Comparative Adhesion Additive Composition No. 8 (CAAC No. 8)

[0081] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 0.36 part of platinum catalyst and 0.24 part of TBT. Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 2.5 parts of SiH polymer and 0.6 part of gamma-glycidoxypolytrimethoxysilane.

[0082] Each of the above compositions were evaluated by mixing 50 weight parts of the contents of Package A with 50 weight parts of the contents of Package B and then forming H-test pieces as shown in the drawings **Fig. 1** and **Fig. 2**.

[0083] In the drawings, **Figure 1** is an end view of an H-test piece. **Figure 2** is a side view of an H-test piece. The following reference numerals are used in the description below:

DRAWING NUMERICAL AND ALPHABETICAL REFERENCE LIST

[0084]

- 10** Glass pane
- 20** Glass pane
- 30** Stainless steel spacer
- 40** Polyisobutylene primary seal
- 50** Polyisobutylene primary seal
- 60** Silicone rubber secondary seal
- 70** Silicone rubber secondary seal
- 80** First direction force is applied during adhesion test
- 90** Second direction force is applied during adhesion test
- L** Length of primary seal and secondary seal
- HP** Height of primary seal
- HS** Height of secondary silicone rubber seal
- W** Width of secondary silicone rubber seal

The H-test pieces were formed by placing stainless steel spacer **30** between two glass panes **10** and **20** with polyisobutylene primary seals **40** and **50** which had heights **HP** of 0.32 cm and lengths **L** of 5 cm. Thereafter, a silicone rubber composition was applied as secondary seals **60** and **70** which had heights **HS** of 0.32 cm, lengths **L** of 5 cm and widths **W** of 0.32 cm. After the H-test piece was formed, it was heated to 80°C. for 15 minutes to cure the silicone rubber composition. Each H-test piece was exposed to various conditions and then tested for adhesion by clamping in a tensile-testing type device. This device pulled the glass panes apart in direction **80** and **90** at the rate of 1.27 cm per minute. The tensile adhesion was measured and reported in Table 2 in newtons (N). The percentage cohesive failure for the stainless steel-silicone rubber interface and for the glass-silicone rubber interface were also recorded and are shown in Table 2. The conditions of exposure were as follows: (1) 1 day at room temperature; (2) 14 days at room temperature; (3) 7 days at room temperature plus 2 weeks immersed in water at 80°C.; and (4) 7 days at room temperature plus 4 weeks immersed in water at 80°C. The test results (an average of three tests) were obtained and reported in Table 2.

[0085] The curing characteristics of the silicone rubber compositions were observed by using a commercially available oscillating rheometer. The results were obtained for cure at room temperature and at 80°C., for each silicone rubber composition after it was prepared (initial) and for each silicone rubber composition stored two weeks at 50°C. before mixing the contents of Package A and Package B (aged). The elapsed times in minutes were observed for each composition to exhibit 50 percent (T_{50}) and 90 percent (T_{90}) of the maximum torque value (F , reported in newton-meters, N-m) which was exhibited by the cured silicone rubber and are reported in Table 3.

TABLE 2

EXPOSURE	TEST OBSERVATIONS	SILICONE RUBBER COMPOSITION									
		AAC NO. 2	AAC NO. 3	AAC NO. 4	AAC NO. 5	AAC NO. 6	AAC NO. 7	AAC NO. 8	CAAC NO. 6	CAAC NO. 7	CAAC NO. 8
(1)	TENSILE-ADHESION, N	151	254	196	138	151	129	151	222	116	147
	ELONGATION, %	48	153	100	24	44	17	38	94	10	8
	COHESIVE FAILURE, % GLASS	100	100	100	100	100	100	100	100	100	100
	COHESIVE FAILURE, % STAINLESS STEEL	25	90	68	2	18	0	23	82	0	0
(2)	TENSILE-ADHESION, N	262	311	338	245	249	240	276	334	151	160
	ELONGATION, %	113	143	154	103	95	85	125	132	18	42
	COHESIVE FAILURE, % GLASS	100	100	100	100	100	100	100	100	100	100
	COHESIVE FAILURE, % STAINLESS STEEL	70	97	98	60	85	57	98	100	0	3

Table 2 (continued)

EXPOSURE	TEST OBSERVATIONS	SILICONE RUBBER COMPOSITION											
		AAC NO. 2	AAC NO. 3	AAC NO. 4	AAC NO. 5	AAC NO. 6	AAC NO. 7	AAC NO. 8	AAC NO. 9	CAAC NO. 6	CAAC NO. 7	CAAC NO. 8	
(3)	TENSILE-ADHESION, N	262	356	387	280	231	125	245	320	298	89	125	
	ELONGATION, %	68	118	128	77	50	15	65	97	82	8	16	
	COHESIVE FAILURE, % GLASS	100	100	100	100	40	3	100	100	100	100	100	
	COHESIVE FAILURE, % STAINLESS STEEL	95	97	98	100	100	95	97	100	90	0	0	
(4)	TENSILE-ADHESION, N	280	307	298	178	240	138	276	298	249	67	107	
	ELONGATION, %	69	98	81	31	54	19	73	79	58	4	12	
	COHESIVE FAILURE, % GLASS	42	100	75	8	20	33	50	98	93	0	0	
	COHESIVE FAILURE, % STAINLESS STEEL	87	98	100	100	100	67	98	87	40	100	100	

[0086] From Table 2, CAAC No. 6 showed that without the presence of the tetrabutyl titanate and comparing it to AAC No. 2, the adhesion to stainless steel at room temperature was very slow to develop and essentially showed no cohesive failure after 14 days at room temperature. CAAC No. 7 and CAAC No. 8 showed that an (epoxy-functional organo)silane with or without tetrabutyl titanate did not provide adhesion to stainless steel at room temperature after 14 days and failed adhesively after hot water immersion either to the glass substrate or to the stainless steel substrate. AAC No. 5 showed that beta(3,4-epoxy cyclohexyl)ethyltrimethoxysilane developed adhesion to both stainless steel and glass between one day and 14 days at room temperature. This showed that the beta(3,4-epoxycyclohexyl)ethyl-trimethoxysilane was not as effective in developing adhesion to stainless steel as gamma-glycidoxypropyltrimethoxysilane as shown for AAC No. 2. AAC No. 9 showed a composition which quickly developed tensile adhesion to both glass substrates and stainless steel substrates. The cure characteristics were as shown in Table 3.

TABLE 3

CURE TEMPER- ATURE	CURE PROPERTIES (INITIAL OR AGED)	SILICONE RUBBER COMPOSITION											
		AAC NO. 2	AAC NO. 3	AAC NO. 4	AAC NO. 5	AAC NO. 6	AAC NO. 7	AAC NO. 8	AAC NO. 9	CAAC NO. 6	CAAC NO. 7	CAAC NO. 8	
80°C	T50 (INT)	1.5	1.6	1.5	1.6	1.1	1.7	2.3	0.5	1.5	0.5	0.5	
	T50 (AGED)	2.5	2.9	2.9	2.7	1.8	4.7	4.1	0.5	1.1	---	---	
	T90 (INT)	2.4	2.6	2.3	2.6	1.9	3.4	3.4	0.9	2.3	1.2	1.2	
	T90 (AGED)	3.8	4.3	4.2	4.0	3.3	8.8	6.9	2.0	2.0	---	---	
	TORQUE, N-m												
	F-INITIAL	3.84	3.78	4.01	3.70	3.95	5.65	4.01	4.57	3.78	4.35	4.35	
	F-AGED	3.50	3.45	3.45	3.45	3.73	5.76	3.84	4.35	3.73	---	---	
ROOM TEMPER- ATURE	I50 (INT)	173	173	178	218	140	308	218	20	178	28	29	
	I90 (INT)	223	225	243	275	195	408	264	43	233	73	70	
	F-INITIAL	3.11	3.28	3.11	3.16	3.16	4.18	3.62	4.12	3.56	4.63	4.63	

Example 3**Adhesion Additive Composition No. 10 (AAC No. 10)**

[0087] Package A was prepared by mixing 92.6 parts of Polymer A, 7.4 parts of Polymer B, 18.5 parts of Silica, 0.5 part of platinum catalyst and 0.3 part of TBT.

[0088] Package B was prepared by mixing 92.6 parts of Polymer A, 7.4 parts of Polymer B, 18.5 parts of silica, 4.2 parts of ethylpolysilicate, 0.5 part of gamma-glycidoxypolytrimethoxy silane, 8.6 parts of SiH polymer and 2.4 parts of diallyl ether of trimethylolpropane.

[0089] A composition was prepared by mixing 50 weight parts of the contents of Package A with 50 weight parts of the contents of Package B. The resulting composition was used to make several H-test pieces as described in Example 2, except that in place of the stainless steel spacer, an aluminum spacer was used and one glass substrate was clear glass and the other glass substrate was a coated glass which had been abraded. The silicone compositions of the H-test pieces was cured by heating to 80°C. for 15 minutes. Test pieces were evaluated after 7 days at room temperature (RT), 14 days at room temperature and after immersion in water at 60°C. for 7 days, 14 days, 28 days, 42 days, 56 days and 70 days. In each situation, the bond failure was 100 % cohesive to the aluminum substrate, the glass substrate and the coated abraded glass substrate. The tensile adhesion in newtons is reported in Table 4:

Table 4

H-TEST PIECE EXPOSURE	TENSILE ADHESION, newtons
7 days RT	464
14 days RT	538
IMMERSION	
7 days	468
14 days	463
28 days	513
42 days	494
56 days	371
70 days	454

Example 4**Adhesion Additive Composition No. 11 (AAC No. 11)**

[0090] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 0.36 part of platinum catalyst, 0.24 part of TBT and 0.6 part of diallyl ether of trimethylolpropane.

[0091] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 3.9 parts of SiH Polymer, 2.6 parts of n-propyl orthosilicate and 0.59 part of gamma-glycidoxypolytrimethoxysilane. The molar ratio of n-propyl orthosilicate to gamma-glycidoxypolytrimethoxysilane was 3.93:1.

Comparative Adhesion Additive Composition No. 9 (CAAC No. 9)

[0092] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 0.35 part of platinum catalyst and 4.0 parts of a pre-reacted mixture (1). The pre-reacted mixture (1) was prepared by mixing 0.19 part of TBT, 0.48 part of gamma-glycidoxypolytrimethoxysilane, 2.12 parts of n-propyl orthosilicate and 0.48 part of diallyl ether of trimethylolpropane, heating the resulting mixture to 90°C. for one hour and then stripping at 90°C. and 12 kPa for 30 minutes. The molar ratio of n-propyl orthosilicate to gamma-glycidoxypolytrimethoxysilane was 3.93:1.

[0093] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica and 3.8 parts of SiH polymer.

Adhesion Additive Composition No. 12 (AAC No. 12)

[0094] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 0.36 part of platinum catalyst and 0.24 part of TBT.

[0095] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 2.8 parts of SiH polymer, 2.6 parts of n-propyl orthosilicate, 0.35 part of gamma-methacryloxypropyltrimethoxysilane and 0.58 part of gamma-glycidoxypolytrimethoxysilane. The molar ratio of n-propyl orthosilicate to gamma-glycidoxypolytrimethoxysilane was 3.93:1.

Comparative Adhesion Additive Composition No. 10 (CAAC No. 10)

[0096] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica and 3.77 parts of pre-reacted mixture (2). The pre-reacted mixture (2) was prepared by mixing 0.23 part of TBT, 2.6 parts of n-propyl orthosilicate, 0.35 part of gamma-methacryloxypropyltrimethoxysilane and 0.59 part of gamma-glycidoxypolytrimethoxysilane, heating the resulting mixture to 90°C. for one hour and stripping at 90°C. and 12 kPa for 30 minutes. The molar ratio of n-propyl ortho silicate to gamma-glycidoxypolytrimethoxysilane was 3.93:1.

[0097] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica and 2.8 parts of SiH polymer.

Comparative Adhesion Additive Composition No. 11 (CAAC No. 11)

[0098] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 0.36 part of Platinum Catalyst, 0.1 part of TBT and 0.7 part of diallyl ether of trimethylolpropane.

[0099] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 4.1 parts of SiH Polymer, 1.7 parts of tetraethyl orthosilicate and 2.4 parts of gamma-glycidoxypolytrimethoxysilane. The molar ratio of tetraethyl orthosilicate to gamma-glycidoxypolytrimethoxysilane was 0.82:1.

Comparative Adhesion Additive Composition No. 12 (CAAC No. 12)

[0100] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 0.36 part of platinum catalyst and 4.9 parts of pre-reacted mixture (3). The pre-reacted mixture (3) was prepared by mixing 0.1 part of TBT, 1.7 parts of tetraethyl orthosilicate, 2.4 parts of gamma-glycidoxypolytrimethoxysilane, 0.7 part of diallyl ether of trimethylolpropane, heating the resulting mixture to 90°C. for one hour and stripping at 90°C. and 12 kPa for 30 minutes. The molar ratio of tetraethyl orthosilicate to gamma-glycidoxypolytrimethoxysilane was 0.82:1.

[0101] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica and 4.1 parts of SiH polymer.

Comparative Adhesion Additive Composition No. 13 (CAAC No. 13)

[0102] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica, 0.36 part of platinum catalyst, 0.08 part of TBT and 0.7 part of diallyl ether of trimethylolpropane.

[0103] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of Silica, 4.0 parts of SiH Polymer, 1.9 parts of n-propyl orthosilicate and 2.2 parts of gamma-glycidoxypolytrimethoxysilane. The molar ratio of n-propyl orthosilicate to gamma-glycidoxypolytrimethoxysilane was 0.8:1.

Comparative Adhesion Additive Composition No. 14 (CAAC No. 14)

[0104] Package A was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica and 4.9 parts of pre-reacted mixture (4). The pre-reacted mixture was prepared by mixing 0.08 part of TBT, 2.2 parts of gamma-glycidoxypolytrimethoxysilane, 1.9 parts of n-propyl orthosilicate and 0.7 part of diallyl ether of trimethylolpropane, heating the resulting mixture to 90°C. for one hour, stripping at 90°C. and 12 kPa for 30 minutes. The molar ratio of n-propyl orthosilicate to gamma-glycidoxypolytrimethoxysilane was 0.8:1.

[0105] Package B was prepared by mixing 94.7 parts of Polymer A, 5.3 parts of Polymer B, 17.9 parts of silica and 4.0 parts of SiH polymer.

[0106] Each of the above compositions were evaluated by preparing H-test pieces as described in Example 2 and by observing the adhesion properties as described in Example 2 where test pieces were evaluated after (1) one day at room temperature, (2) 14 days at room temperature, (3) 7 days at room temperature and 14 days immersion in water at 80°C. and (4) 7 days at room temperature and 28 days immersion in water at 80°C. The curing characteristics of each composition was evaluated as described in Example 2. The results of the evaluations are shown in Tables 5 and 6.

Table 5

EXPOSURE	TEST OBSERVATIONS	SILICONE RUBBER COMPOSITION									
		AAC NO. 11	CAAC NO. 9	AAC NO. 12	CAAC NO. 10	CAAC NO. 11	CAAC NO. 12	CAAC NO. 13	CAAC NO. 14		
(1)	TENSILE-ADHESION, N	294	173*	245	142	157	157*	157	138*		
	ELONGATION, %	148	71	127	44	61	81	52	46		
	COHESIVE FAILURE, % GLASS	100	100	100	100	100	100	100	100		
	COHESIVE FAILURE, % STAINLESS STEEL	88	42	80	2	5	47	17	2		
(2)	TENSILE-ADHESION, N	427	289*	369	205*	302	302*	356	271*		
	ELONGATION, %	179	144	148	82	143	164	157	139		
	COHESIVE FAILURE, % GLASS	100	100	100	100	100	100	100	100		
	COHESIVE FAILURE, % STAINLESS STEEL	100	92	100	60	88	100	98	98		

Table 5 (continued)

EXPOSURE	TEST OBSERVATIONS	SILICONE RUBBER COMPOSITION							
		AAC NO. 11	CAAC NO. 9	AAC NO. 12	CAAC NO. 10	CAAC NO. 11	CAAC NO. 12	CAAC NO. 13	CAAC NO. 14
(3)	TENSILE-ADHESION, N	356	245*	227	187*	129	133*	107	138*
	ELONGATION, %	113	92	50	55	18	16	11	20
	COHESIVE FAILURE, % GLASS	90	100	0	50	0	0	0	0
	COHESIVE FAILURE, % STAINLESS STEEL	100	93	100	70	100	100	100	100
(4)	TENSILE-ADHESION, N	191	200*	182	160*	111	93*	98	102*
	ELONGATION, %	39	50	39	31	10	12	11	11
	COHESIVE FAILURE, % GLASS	50	58	20	0	0	0	0	0
	COHESIVE FAILURE, % STAINLESS STEEL	100	100	100	100	100	100	100	100

*Bubble formation was observed at the interface between the polyisobutylene primary seals 40 and 50 and the silicone rubber secondary seals 60 and 70.

TABLE 6

CURE TEMPER- ATURE	CURE PROPERTIES INITIAL	SILICONE RUBBER COMPOSITION							
		AAC NO. 11	CAAC NO. 9	AAC NO. 12	CAAC NO. 10	CAAC NO. 11	CAAC NO. 12	CAAC NO. 13	CAAC NO. 14
80°C	T50 (INT)	0.9	0.7	0.6	0.4	1.0	0.5	1.3	0.4
	T90 (INT)	1.8	1.5	1.5	0.9	2.2	1.0	3.9	0.75
	TORQUE, N-m F-INITIAL	4.18	4.07	4.29	4.18	4.01	3.95	3.84	3.95
ROOM TEMPER- ATURE	T50 (INT)	98	61	40	45	113	48	143	48
	T90 (INT)	148	108	83	125	160	80	208	83
	F-INITIAL	4.07	3.73	4.24	3.62	3.73	3.62	3.62	3.67

[0107] Pre-reacting the ingredients added to provide adhesion to the silicone compositions did not provide satisfactory wet adhesion as shown by CAAC No. 10, CAAC No. 12 and CAAC No. 14. Also, CAAC No. 11 and CAAC No. 13 illustrated the need to have the moles of alkoxysilicon compound exceed the moles of (epoxy-functional organo)-

trialkoxysilane.

Claims

1. A silicone composition curable to a rubber comprising


(A) 100 parts by weight of an alkenyl-containing polydiorganosiloxane having an average of at least two silicon-bonded alkenyl radicals per molecule where the alkenyl radical has from 2 to 10 carbon atoms per radical, each organo radical of the polydiorganosiloxane being a monovalent radical selected from hydrocarbon radicals and fluorinated alkyl radicals both having less than 7 carbon atoms per radical, the polydiorganosiloxane having triorganosiloxy endgroups,

(B) an organohydrogensiloxane having an average of at least three silicon-bonded hydrogen atoms per molecule and valences of any silicon atom in the organohydrogensiloxane not satisfied by a hydrogen atom is satisfied by a divalent oxygen atom or an organo radical, wherein each organo radical is a monovalent radical selected from hydrocarbon radicals and fluorinated alkyl radicals both having less than 7 carbon atoms per radical, the organohydrogensiloxane having no more than one silicon-bonded hydrogen atom on any one silicon atom, the amount of organohydrogensiloxane providing a ratio of silicon-bonded hydrogen atoms to alkenyl groups from the polydiorganosiloxane of 1.2 to 2,

(C) a hydrosilation catalyst containing platinum,

(D) 0.1 to 1 part by weight of an (epoxy-functional organo)trialkoxysilane where the alkoxy radicals of the (epoxy-functional organo)trialkoxysilane have 1 to 4 inclusive carbon atoms,

(E) 0.25 to 5 parts by weight of an alkoxy silicon compound selected from tetraalkyl orthosilicates, alkyl polysilicates and alkoxy silicon compounds of the general formula



wherein n is 0 or 1, R is an alkyl radical of 1 to 4 inclusive carbon atoms and R' is a monovalent hydrocarbon radical, where the alkyl groups of the tetraalkyl orthosilicates and the alkyl polysilicates are methyl, ethyl, propyl or butyl, and

(F) 0.01 to 0.5 part by weight of a titanium compound having Ti-O-CH bonds,

where the total amount of ingredient (D) and ingredient (E) is from 0.5 to 6 parts by weight and the molar amount of (E) exceeds the molar amount of (D).

2. The silicone composition according to claim 1 further comprising (G) at least 0.1 part by weight of a gamma-methacryloxypropyltrialkoxysilane in which the alkoxy has from 1 to 4 inclusive carbon atoms per alkoxy group.

3. The silicone composition according to claim 1 further comprising diallyltrimethylol propane ether.

4. A method of adhering a glass substrate to a stainless steel substrate comprising

(1) preparing the silicone composition of claim 1,

(2) applying said composition to a glass substrate and a stainless steel substrate such that the glass and stainless steel substrates are connected by said composition to form an assembly, and thereafter

(3) maintaining the assembly in position until the silicone rubber composition has cured, thereby bonding the glass substrate to the stainless steel substrate through cured silicone rubber.

5. The method according to claim 4 further comprising a thermoplastic material in combination with the glass substrate, stainless steel substrate and curable silicone rubber composition such that the curable silicone rubber composition contacts the thermoplastic material, the glass substrate and the stainless steel substrate during step

(3) and the assembly is heated to accelerate curing.

Patentansprüche

1. Siliconzusammensetzung, die zu einem Kautschuk härter ist, enthaltend:


(A) 100 Gewichtsteile eines alkenylhaltigen Polydiorganosiloxans mit im Mittel wenigstens zwei an Silicium gebundenen Alkenylresten pro Molekül, wobei die Alkenylreste 2 bis 10 Kohlenstoffatome pro Rest aufweisen, jeder Organorest des Polydiorganosiloxans ein einbindiger Rest ist, ausgewählt aus Kohlenwasserstoffresten und fluorierten Alkylresten, die beide weniger als 7 Kohlenstoffatome pro Rest aufweisen, und das Polydiorganosiloxan Triorganosiloxyendgruppen aufweist,

(B) ein Organowasserstoffsiloxan mit im Mittel wenigstens drei an Silicium gebundenen Wasserstoffatomen pro Molekül, wobei die Valenzen eines jeden Siliciumatoms in dem Organowasserstoffsiloxan, die nicht durch ein Wasserstoffatom abgesättigt sind, durch ein zweibindiges Sauerstoffatom oder einen Organorest abgesättigt sind, wobei jeder Organorest ein einbindiger Rest ist, ausgewählt aus Kohlenwasserstoffresten und fluorierten Alkylresten, wobei beide weniger als 7 Kohlenstoffatome pro Rest aufweisen, das Organowasserstoffsiloxan nicht mehr als ein an Silicium gebundenes Wasserstoffatom pro Siliciumatom aufweist und die Menge an Organowasserstoffsiloxan ein Verhältnis von an Silicium gebundenen Wasserstoffatomen zu Alkenylgruppen aus dem Polydiorganosiloxan von 1,2 bis 2 bereitstellt,

(C) einen Hydrosilylierungskatalysator, der Platin enthält,

(D) 0,1 bis 1 Gewichtsteil eines Trialkoxysilans mit einer epoxifunktionellen Organogruppe, wobei die Alkoxyreste des Trialkoxysilans mit einer epoxifunktionellen Organogruppe 1 bis einschließlich 4 Kohlenstoffatome aufweisen,

(E) 0,25 bis 5 Gewichtsteile einer Alkoxysiliciumverbindung, ausgewählt aus Tetraalkylorthosilicaten, Alkylpolyisilicaten und Alkoxysiliciumverbindungen der allgemeinen Formel



worin n gleich 0 oder 1 ist, R ein Alkylrest mit 1 bis einschließlich 4 Kohlenstoffatomen ist und R' ein einbindiger Kohlenwasserstoffrest ist, wobei die Alkylgruppen des Tetraalkylorthosilicats und des Alkylpolyisilicats Methyl, Ethyl, Propyl oder Butyl sind, und

(F) 0,01 bis 0,5 Gewichtsteile einer Titanverbindung mit Ti-O-CH-Bindungen,

wobei die Gesamtmenge des Bestandteils (D) und des Bestandteils (E) 0,5 bis 6 Gewichtsteile beträgt und die molare Menge an (E) die molare Menge an (D) überschreitet.

2. Siliconzusammensetzung nach Anspruch 1, die weiterhin (G) wenigstens 0,1 Gewichtsteile eines γ -Methacryloxypropyltrialkoxysilans enthält, in dem die Alkoxygruppe 1 bis einschließlich 4 Kohlenstoffatome pro Alkoxygruppe aufweist.

3. Siliconzusammensetzung nach Anspruch 1, die weiterhin Diallyltrimethylolpropanether enthält.

4. Verfahren zum Ankleben eines Glassubstrats an ein Edelstahlsubstrat, umfassend

(1) Herstellung der Siliconzusammensetzung nach Anspruch 1,

(2) Aufbringen dieser Zusammensetzung auf ein Glassubstrat und ein Edelstahlsubstrat, so daß die Glas- und Edelstahlsubstrate durch diese Zusammensetzung miteinander verbunden werden, um eine zusammengesetzte Anordnung zu bilden, und danach

(3) in Position halten der zusammengesetzten Anordnung, bis die Siliconkautschukzusammensetzung ausgehärtet ist, um dadurch das Glassubstrat an das Edelstahlsubstrat durch den gehärteten Siliconkautschuk

zu binden.

5. Verfahren nach Anspruch 4, das weiterhin ein thermoplastisches Material in Kombination mit dem Glassubstrat, dem Edelstahlsubstrat und der härtbaren Siliconkautschukzusammensetzung umfaßt, so daß die härtbare Siliconkautschukzusammensetzung in Kontakt mit dem thermoplastischen Material, dem Glassubstrat und dem Edelstahlsubstrat während des Schritts (3) steht und die zusammengesetzte Anordnung erwärmt wird, um das Aushärten zu beschleunigen.

Revendications

1. Une composition de silicone durcissable en un caoutchouc comprenant


(A) 100 parties en poids d'un polydiorganosiloxane contenant des groupes alcényles, ayant en moyenne au moins deux radicaux alcényles liés au silicium par molécule, le radical alcényle ayant 2 à 10 atomes de carbone par radical, chaque radical organique du polydiorganosiloxane étant un radical monovalent choisi parmi les radicaux hydrocarbonés et les radicaux alkyles fluorés qui ont tous moins de 7 atomes de carbone par radical, le polydiorganosiloxane ayant des groupes terminaux triorganosiloxy,

(B) un organohydrogénosiloxane ayant en moyenne au moins trois atomes d'hydrogène liés au silicium par molécule et où les valences de tout atome de silicium de l'organohydrogénosiloxane non satisfaites par un atome d'hydrogène sont satisfaites par un atome d'oxygène divalent ou un radical organique, chaque radical organique étant un radical monovalent choisi parmi les radicaux hydrocarbonés et les radicaux alkyles fluorés qui ont tous moins de 7 atomes de carbone par radical, l'organohydrogénosiloxane n'ayant pas plus d'un atome d'hydrogène lié au silicium sur chaque atome de silicium, la quantité d'organohydrogénosiloxane établissant un rapport des atomes d'hydrogène liés au silicium aux radicaux alcényles du polydiorganosiloxane de 1,2 à 2,

(C) un catalyseur d'hydrosilylation contenant du platine,

(D) 0,1 à 1 partie en poids d'un (organo à fonction époxy)trialcoxysilane où les groupes alcoxy du (organo à fonction époxy)trialcoxysilane ont 1 à 4 atomes de carbone inclusivement,

(E) 0,25 à 5 parties en poids d'un composé alcoxy-silicié choisi parmi les orthosilicates de tétraalkyle, les polysilicates d'alkyle et les composés alcoxysiliciés de la formule générale



où n est 0 ou 1, R est un radical alkyle de 1 à 4 atomes de carbone inclusivement et R' est un radical hydrocarboné monovalent, les radicaux alkyles des orthosilicates de tétraalkyle et des polysilicates d'alkyle étant des radicaux méthyle, éthyle, propyle ou butyle, et

(F) 0,01 à 0,5 partie en poids d'un composé du titane ayant des liaisons Ti-O-CH,

la quantité totale de l'ingrédient (D) et de l'ingrédient (E) étant de 0,5 à 6 parties en poids et la quantité molaire de (E) dépassant la quantité molaire de (D).

2. La composition de silicone selon la revendication 1, comprenant de plus (G) au moins 0,1 partie en poids d'un gamma-méthacryloxypropyltrialcoxysilane dans lequel le groupe alcoxy compte 1 à 4 atomes de carbone inclusivement par groupe alcoxy.
3. La composition de silicone selon la revendication 1, comprenant de plus de l'éther diallylique de triméthylolpropane.
4. Un procédé pour coller un substrat en verre à un substrat en acier inoxydable, consistant à

(1) préparer la composition de silicone de la revendication 1,

(2) appliquer ladite composition à un substrat en verre et à un substrat en acier inoxydable de telle manière que les substrats en verre et en acier inoxydable soient joints par ladite composition pour former un assemblage, puis

5 (3) maintenir l'assemblage en position jusqu'à ce que la composition de caoutchouc de silicone ait durci, pour lier ainsi le substrat en verre au substrat en acier inoxydable au moyen du caoutchouc de silicone durci.

5. Le procédé selon la revendication 4, comprenant de plus une matière thermoplastique en association avec le substrat en verre, le substrat en acier inoxydable et la composition de caoutchouc de silicone durcissable, de sorte
10 que la composition de caoutchouc de silicone durcissable soit en contact avec la matière thermoplastique, le substrat en verre et le substrat en acier inoxydable pendant l'étape (3), et le chauffage de l'assemblage pour accélérer le durcissement.

15

20

25

30

35

40

45

50

55

Fig. 1




Fig. 2

